

Material: AFNOR NF 1.7189

Standard Specification for Mild Steel Alloys Bar and Rod

Group: Ferrous Mild Steel Alloys

Sub Group: AFNOR NF 1.7189 Mild Steel Alloys Bar and Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.360 - 0.420	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	1.400 - 1.700		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.300 - 0.600		
Boron	B %	0.0008 - 0.0050		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 1000 - 1350 Yield Strength in Mpa 800 min. Elongation in % 12 min. Reduction of Area in % 50 min. Hardness in BHN 255 max. Impact in Joule 40 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
39MnCrB6-2	EN	European Union	Bar and Rod
1.7189	EN	European Union	Bar and Rod
39MnCrB6-2	ISO	International	Bar and Rod
39MnCrB6-2	AFNOR NF	France	Bar and Rod
1.7189	BS	British	Bar and Rod
39MnCrB6-2	BS	British	Bar and Rod
1.7189	NBN	Belgium	Bar and Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com