

Material: AFNOR NF CW509L

Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose

Group: Non Ferrous Copper Alloys

Sub Group: AFNOR NF CW509L Copper and Copper Alloy Rod for Free Machining Purpose

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.050 max.	As Raw or Solution Heat Treated	
Lead	Pb %	0.200 max.		
Iron	Fe %	0.200 max.		
Nickel	Ni %	0.300 max.		
Other	Ot %	0.200 max.		
Copper	Cu %	59.000 - 61.500		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 289.3 - 588.4 Yield Strength in Mpa 86 min. Elongation in % 4 min. Reduction of Area in % - Hardness in HV 75 - 160 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 12164 CuZn39Pb2	DIN	Germany	Rod
M059	PN	Poland	Rod
B 124 CW612N	ASTM	USA	Rod
Ms58	DIN	Germany	Rod
CZ 120	BS	British	Rod
C37700	UNS	USA	Rod
CuZn40	AFNOR NF	France	Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com