

Material: AFNOR NF EN 1982 CB762S

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group: Non-Ferrous Copper Alloy

Sub Group: AFNOR NF EN 1982 Copper and Copper Alloys - Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	4.000 - 7.000	As-Cast	
Iron	Fe %	1.500 - 3.500		
Manganese	Mn %	3.000 - 5.000		
Nickel	Ni %	2.700 max.		
Phosphorus	P %	0.020 max.		
Lead	Pb %	0.200 max.		
Antimony	Sb %	0.030 max.		
Silicon	Si %	0.080 max.		
Tin	Sn %	0.200 max.		
Cu + Ni	Cu%+Ni%	60.000 - 66.000		
Zinc	Zn %	Balance	Mechanical Properties Tensile Strength in Mpa 680 - 750 Yield Strength in Mpa 450 - 580 Elongation in % 1 - 8 Reduction of Area in % - Hardness in HB 180 - 190 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC762S	BS	British	Ingot and Casting
CB762S	MSZ	Hungary	Ingot and Casting
CB762S	ONORM	Australia	Ingot and Casting
CB762S	DIN	Germany	Ingot and Casting
CuZn25Al5MnFe3-C	DIN	Germany	Ingot and Casting
CuZn25Al5Mn4Fe3-B	DIN	Germany	Ingot and Casting
CuZn25Al5Mn4Fe3-B	UNI	Italy	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com