

Material: AFNOR NF EN 1982 CC765S

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group: Non-Ferrous Copper Alloy

Sub Group: AFNOR NF EN 1982 Copper and Copper Alloys - Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.500 - 2.500	As-Cast	
Iron	Fe %	0.500 - 2.000		
Manganese	Mn %	0.500 - 3.000		
Nickel	Ni %	6.000 max.		
Phosphorus	P %	0.030 max.		
Lead	Pb %	0.500 max.		
Antimony	Sb %	0.080 max.		
Silicon	Si %	0.010 max.		
Tin	Sn %	1.000 max.		
Cu + Ni	Cu%+Ni%	57.000 - 65.000		
Zinc	Zn %	Balance	Mechanical Properties Tensile Strength in Mpa 450 - 500 Yield Strength in Mpa 170 - 200 Elongation in % 18 - 20 Reduction of Area in % - Hardness in HB 110 - 120 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CB765S	BS	British	Ingot and Casting
CC765S	BDS	Bulgaria	Ingot and Casting
CC765S	CSN	Czech Republic	Ingot and Casting
CC765S	DIN	Germany	Ingot and Casting
CuZn35Mn2Al1Fe1-C	UNI	Italy	Ingot and Casting
CuZn35Mn2Al1Fe1-C	UNE	Spain	Ingot and Casting
CuZn35Mn2Al1Fe1-C	MSZ	Hungary	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com