

Material: AISI 8625

Standard Specification for Alloy Steel Casting

Group: Ferrous Mild Steel Alloys

Sub Group: AISI 8625 Alloy Steel Casting, Bar, Wire, Tube and Forging

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar, Wire, Tube and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.230 - 0.280	As- Cast or Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.150 - 0.350		
Manganese	Mn %	0.700 - 0.900		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	0.400 - 0.600		
Molybdenum	Mo %	0.150 - 0.250		
Nickel	Ni %	0.400 - 0.700		
Copper	Cu %	0.350 max.		
Vanadium	V %	0.050 max.	Mechanical Properties	
Aluminium	Al %	0.020 max.	Tensile Strength in Mpa	480 - 965
Niobium	Nb %	0.025 max.	Yield Strength in Mpa	-
Iron	Fe %	Balance	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	179 - 223
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A915 Grade SC 8625	UNS	USA	Casting
J12595	UNS	USA	Bar, Wire, Tube and Forging
A 29 8625	ASTM	USA	Bar, Wire, Tube and Forging
A 505 8625	ASTM	USA	Bar, Wire, Tube and Forging
8625	SAE	USA	Bar, Wire, Tube and Forging
8625	AMS	USA	Bar, Wire, Tube and Forging
8625	AS	Australia	Bar, Wire, Tube and Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com