

Material: AMS 5400

Standard Specification for Steel, Corrosion Resistant, Investment Casting

Group: Ferrous Stainless Steel Alloys

Sub Group: AMS 5400 Steel, Corrosion Resistant, Investment Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.500 - 1.000		
Manganese	Mn %	0.600 max.		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	14.000 - 15.500		
Nickel	Ni %	4.200 - 5.000		
Copper	Cu %	2.500 - 3.200		
Nitrogen	N %	0.050 max.		
Tantalum	Ta %	0.050 max.	Mechanical Properties	
Niobium	Nb %	0.150 - 0.300	Tensile Strength in Mpa	1172 min.
Iron	Fe %	Balance	Yield Strength in Mpa	1034 min.
-	-	-	Elongation in %	6 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	38-47
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J92110	UNS	USA	Casting
UNS J92130	UNS	USA	Casting
SA-747 CB7Cu-2	ASME	USA	Casting
5356	AMS	USA	Casting
AMS 5346	SAE	USA	Casting
5357	AMS	USA	Casting
A747 CB7CU-2	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com