

Material: AMS 5764

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: AMS 5764 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel, Bar, Wire, Extrusion and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	4.000 - 6.000		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	20.500 - 23.500		
Molybdenum	Mo %	1.500 - 3.000		
Nickel	Ni %	11.500 - 13.500		
Titanium	Ti %	0.020 max.		
Zirconium	Zr %	0.020 max.		
			Mechanical Properties	
Aluminium	Al %	0.020 max.	Tensile Strength in Mpa	690 min.
Nitrogen	N %	0.200 - 0.400	Yield Strength in Mpa	379 min.
Iron	Fe %	Balance	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	20 min.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S20910	ASTM	USA	Steel, Plate, Sheet and Strip
20910	UNS	USA	Steel
XM-19	SAE	USA	Steel
A358 XM-19	ASTM	USA	Steel and Pipe
A479 XM-19	ASTM	USA	Steel and Bar
A182 F XM-19	ASTM	USA	Steel, Pipe and Forging
A314 XM-19	ASTM	USA	Steel, Rolling and Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com