

Material: ANSI AA 390.0

Standard Specification for Aluminium and Aluminium Alloys Ingot and Casting

Group: Non-Ferrous Aluminium Alloy

Sub Group: ANSI AA 390.0 Aluminium and Aluminium Alloys Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	4.000 - 5.000	As-Cast	
Iron	Fe %	1.300 max.		
Magnesium	Mg %	0.450 - 0.656		
Manganese	Mn %	0.100 max.		
Silicon	Si %	16.000 - 18.000		
Titanium	Ti %	0.200 max.		
Zinc	Zn %	0.100 max.		
Other	Ot%	0.200 max.		
Aluminium	Al %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	150 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRB	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LM30	BS	British	Ingot and Casting
ADC 14	JIS	Japan	Casting
AC-48100	EN	European Union	Casting
EN AC-48100	DIN	Germany	Casting
AlSi17Cu4Mg	ISO	International	Casting
ALDC 14	JIS	Japan	Casting
EN AC-48100	UNE	Spain	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com