

Material: ANSI AA A384.0

Standard Specification for Aluminium and Aluminium Alloys Ingot and Casting

Group: Non-Ferrous Aluminium Alloy

Sub Group: ANSI AA A384.0 Aluminium and Aluminium Alloys - Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	3.000 - 4.500	As-Cast	
Magnesium	Mg %	0.100 max.		
Silicon	Si %	10.500 - 12.000		
Iron	Fe %	1.300 max.		
Manganese	Mn %	0.500 max.		
Nickel	Ni %	0.500 max.		
Zinc	Zn %	1.000 max.		
Tin	Sn %	0.350 max.		
Other	Ot%	0.500 max.		
Aluminium	Al %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	140 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	1 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LM27	BS	British	Ingot and Casting
AS315	AS	Australia	Ingot and Casting
AA315	AS	Australia	Ingot and Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com