

# Material: ANSI/AA F3N.20S-F

## Specification Standards for Die Castings

**Group:** Non-Ferrous Aluminium Alloy Sub

**Group:** ANSI/AA for Die Castings

**Application :** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Casting

Chemical Composition			Heat Treatment	
Silicon	Si %	9.500 - 10.500	As-Cast	
Iron	Fe %	0.800 - 1.200		
Copper	Cu %	0.200 max.		
Magnesium	Mg %	0.500 - 0.700		
Manganese	Mn %	0.500 - 0.800		
Titanium	Ti %	0.200 max.		
Zinc	Zn %	0.050 max.		
Other	Ot%	0.100 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	303 min.
			Yield Strength in Mpa	248 min
			Elongation in %	0.5 min.
			Reduction of Area in %	-
			Hardness in HRB	73 min.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: info@icastllp.com