

Material: ANSI/AA Zamak 2

Specification Standards for Die Castings

Group: Non-Ferrous Zinc Alloy

Sub Group: ANSI/AA for Die Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.700 - 4.300	As-Cast or Aging	
Magnesium	Mg %	0.020 - 0.060		
Copper	Cu %	2.600 - 3.300		
Iron	Fe %	0.050 max.		
Lead	Pb %	0.005 max.		
Cadmium	Cd %	0.004 max.		
Tin	Sn %	0.002 max.		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	359 min.
-	-	-	Yield Strength in Mpa	283 min
-	-	-	Elongation in %	7 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	100 min.
-	-	-	Impact in Joule	47.5 min.

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ZDC 2	JIS	Japan	Casting
ZDC 2	KS	Korea	Casting
B240 AG40A	ASTM	USA	Casting
B240 Zamak 3	ASTM	USA	Casting
GD-ZnAl4	DIN	Germany	Casting
ZL3	ISO	International	Casting
903	SAE	USA	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com