

Material: AS 2074/H3CM

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: AS 2074/H3CM Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As Cast or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	11.500 - 13.500		
Nickel	Ni %	3.400 - 4.200		
Molybdenum	Mo %	0.600 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	770 min.
-	-	-	Yield Strength in Mpa	620 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	235 - 321
-	-	-	Impact in Joule	25 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
425C11	BS	British	Casting
2074/H3C	AS	Australia	Casting
Z 4 CN 13.4 M	AFNOR NF	France	Casting
Z 4 CND 13.4 M	AFNOR NF	France	Casting
1.4313	EN	European Union	Casting
X3CrNiMo13-4	EN	European Union	Casting
1.4313	AFNOR NF	France	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com