

Material: AS 2074/L5H

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: AS 2074/L5H Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.100 - 0.150
Silicon	Si %	0.450 max.
Manganese	Mn %	0.400 - 0.700
Phosphorus	P %	0.030 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	0.300 - 0.500
Molybdenum	Mo %	0.400 - 0.600
Nickel	Ni %	0.300 max.
Copper	Cu %	0.300 max.
Tin	Sn %	0.050 max.
Vanadium	V %	0.220 - 0.350
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment
As Cast or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	510 min.
Yield Strength in Mpa	295 min.
Elongation in %	17 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B7	BS	British	Casting
660	BS	British	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India