

Material: AS 485

Standard Specification for Copper and Copper Alloy - Forging Stock and Forgings

Group: Non Ferrous Copper Alloys

Sub Group: AS 485 Copper and Copper Alloy - Forging Stock and Forgings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Forging

Heat Treatment

Mechanical Properties	
Tensile Strength in Mpa	320 min.
Yield Strength in Mpa	-
Elongation in %	20 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuZn36Pb2Sn1	DIN	Germany	Rod
B 21 C48500	ASTM	USA	Rod, Bar and Shape
B 124 C48500	ASTM	USA	Rod, Bar and Shape
B 283 C48500	ASTM	USA	Forging
SB-283 C48500	ASME	USA	Forging
2.0371	DIN	Germany	Rod
C48500	AS	Australia	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com