

Material: AS/NZS 1568 C36500

Standard Specification for Copper and Copper-Alloy Forgings

Group: Non-Ferrous Copper Alloy

Sub Group: AS/NZS 1568 Copper and Copper-Alloy Forgings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Forging

Chemical Composition			Heat Treatment	
Iron	Fe %	0.150 max.	Normalizing or Annealing or Tempering	
Lead	Pb %	0.250 - 0.700		
Tin	Sn %	0.250 max.		
Copper	Cu %	58.000 - 61.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	310 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B171 C36500	ASTM	USA	Plate and Sheet
B283 C36500	ASTM	USA	Forging
SB-171 C36500	ASME	USA	Plate and Sheet
SB-283 C36500	ASME	USA	Forging
365	AS	Australia	Forging
C36500	UNS	USA	Rod, Bar and Shapes
B124 C36500	ASTM	USA	Rod, Bar and Shapes

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com