

Material: ASME SA-351 CH10

Standard Specification for Steel Castings for Valves, Flanges, Fittings, and Other Pressure-Containing Parts

Group: Ferrous Stainless Steel Alloys

Sub Group: ASME SA-351 CH10 Steel Castings for Valves, Flanges, Fittings, and Other Pressure-Containing Parts

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.040 - 0.100
Silicon	Si %	2.000 max.
Manganese	Mn %	1.500 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.040 max.
Chromium	Cr %	22.000 - 26.000
Nickel	Ni %	12.000 - 15.000
Molybdenum	Mo %	0.500 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
Solution Annealing	

Mechanical Properties	
Tensile Strength in Mpa	485 min.
Yield Strength in Mpa	205 min.
Elongation in %	30 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J93401	UNS	USA	Casting
1.4950	EN	European Union	Flat Products Made of Steels for Pressure Purpose
309S	AISI	USA	Bar, Wire, Strip, Plat, Sheet and Forging
SUS 309 STB	JIS	Japan	Superheater, Tubes of Boiler and Heat Exchangers
X 6 CrNi 23-14	UNI	Italy	Plate, Sheets, Strip and Coil
A743 CH10	ASTM	USA	Casting
A351 CH10	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India