

Material: ASME SA-352 LCA

Standard Specification for Castings for Valves, Flanges, Fittings, and Other Pressure Containing Parts

Group: Ferrous Mild Steel Alloys

Sub Group: ASME SA-352 LCA Castings for Valves, Flanges, Fittings, and Other Pressure Containing Parts

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 max.	Normalizing + Tempering or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.700 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.045 max.		
Chromium	Cr %	0.500 max.		
Nickel	Ni %	0.500 max.		
Molybdenum	Mo %	0.200 max.		
Vanadium	V %	0.030 max.		
Copper	Cu %	0.300 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 415 - 585 Yield Strength in Mpa 205 min. Elongation in % 24 min. Reduction of Area in % 35 min. Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J02504	UNS	USA	Casting
J02502	UNS	USA	Casting
A352 LCA	ASTM	USA	Casting
1.0619	EN	European Union	Casting
1.0619	DIN	Germany	Casting
A216 WCB	ASTM	USA	Casting
SA-216 WCB	ASME	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com