

Material: ASME SA-487 6A

Standard Specification for Low Alloy Steel and Martensitic Stainless Steel Castings Suitable for Pressure Containing Parts

Group: Ferrous Mild Steel Alloys

Sub Group: ASME SA-487 6A Low Alloy Steel and Martensitic Stainless Steel Castings Suitable for Pressure Containing Parts

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.050 - 0.380
Silicon	Si %	0.800 max.
Manganese	Mn %	1.300 - 1.700
Phosphorus	P %	0.040 max.
Sulphur	S %	0.045 max.
Chromium	Cr %	0.400 - 0.800
Nickel	Ni %	0.400 - 0.800
Molybdenum	Mo %	0.300 - 0.400
Copper	Cu %	0.500 max.
Vanadium	V %	0.030 max.
Tungsten	W %	0.100 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment	
Annealing or Normalizing or Hardening + Tempering	

Mechanical Properties	
Tensile Strength in Mpa	795 min.
Yield Strength in Mpa	550 min.
Elongation in %	18 min.
Reduction of Area in %	30 min.
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Fe E 420	UNI	Italy	Steel
J13855	UNS	USA	Casting
SA-487 6B	ASME	USA	Casting
A487 6A	ASTM	USA	Casting
A487 6B	ASTM	USA	Casting
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com