

Material: ASME SA-494 M-25S Class 3

Standard Specification for Castings, Nickel and Nickel Alloy

Group: Non-Ferrous Nickel Alloys

Sub Group: ASME SA-494 M-25S Class 3 Castings, Nickel and Nickel Alloy

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	3.500 - 4.500		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Iron	Fe %	3.500 max.		
Copper	Cu %	27.000 - 33.000		
Nickel	Ni %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	300 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A 494 M25S	ASTM	USA	Casting
N24025	UNS	USA	Casting
SA-494 M-25S Class 1	ASME	USA	Casting
SA-494 M-25S Class 2	ASME	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com