

Material: ASME SB-573 N10242

Standard Specification for Nickel-Molybdenum-Chromium-Iron Alloys Rod

Group: Non-Ferrous Nickel Alloys

Sub Group: ASME SB-573 N10242 Nickel-Molybdenum-Chromium-Iron Alloys Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.800 max.		
Manganese	Mn %	0.800 max.		
Copper	Cu %	0.500 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	7.000 - 9.000		
Phosphorus	P %	0.030 max.		
Molybdenum	Mo %	24.000 - 26.000		
Cobalt	Co %	1.000 max.	Mechanical Properties	
Aluminium	Al %	0.500 max.	Tensile Strength in Mpa	725 min.
Boron	B %	0.006 max.	Yield Strength in Mpa	310 min.
Iron	Fe %	2.000 max.	Elongation in %	40 min.
Nickel	Ni %	Balance	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 434 N10242	ASTM	USA	Plate, Sheet and Strip
B 564 N10242	ASTM	USA	Forging
B 573 N10242	ASTM	USA	Rod
B 619 N10242	ASTM	USA	Pipe
B 622 N10242	ASTM	USA	Pipe and Tube
B 626 N10242	ASTM	USA	Tube
SB-619 N10242	ASME	USA	Pipe

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com