

Material: ASME SB-688 N08366

Standard Specification for Chromium-Nickel-Molybdenum-Iron Plate, Sheet and Strip

Group: Non-Ferrous Nickel Alloys

Sub Group: ASME SB-688 N08366 Chromium-Nickel-Molybdenum-Iron Plate, Sheet and Strip

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.035 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Chromium	Cr %	20.000 - 22.000		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	6.000 - 7.000		
Phosphorus	P %	0.040 max.		
Nickel	Ni %	23.500 - 25.500		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	515 min.
			Yield Strength in Mpa	240 min.
			Elongation in %	30 min.
			Reduction of Area in %	-
			Hardness in BHN	212 max.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 688 N08366	ASTM	USA	Plate, Sheet and Strip
B 691 N08366	ASTM	USA	Rod, Bar and Wire
B 690 N08366	ASTM	USA	Pipe and Tube
SB-690 N08366	ASME	USA	Pipe and Tube
SB-691 N08366	ASME	USA	Rod, Bar and Wire
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com