

Material: ASTM A 1040 1044

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 1040 1044 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition		
Carbon	C %	0.430 - 0.500
Manganese	Mn %	0.300 - 0.600
Phosphorus	P %	0.040 max.
Sulphur	S %	0.050 max.
Copper	Cu %	0.200 max.
Silicon	Si %	0.100 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Raw or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	550 min.
Yield Strength in Mpa	300 min.
Elongation in %	16 min.
Reduction of Area in %	40 min.
Hardness in HB	163 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10440	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1044	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1044	AISI	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
M1044	SAE	USA	Steel
M1044	AISI	USA	Steel
A 29 1044	ASTM	USA	Steel and Bar
A 575 M1044	ASTM	USA	Steel and Bar

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India