

Material: ASTM A 1040 1074

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Steel

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 1040 1074 Carbon Steel Compositions For Forging To Hot-Rolled Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.700 - 0.800	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.035 max.		
Copper	Cu %	0.200 Min.		
Boron	B %	0.0005 - 0.003		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 650 - 720 Yield Strength in Mpa 400 min. Elongation in % 10 min. Reduction of Area in % 30 - 40 Hardness in HB 192 - 217 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10740	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1074	SAE	USA	Steel
1074	AISI	USA	Steel and Bar
A 29 1074	ASTM	USA	Steel and Bar
A 510 1074	ASTM	USA	Steel
A 682 G10740	ASTM	USA	Steel and Strip
A 682 Grade 1074	ASTM	USA	Steel and Strip

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com