

Material: ASTM A 182 F 429

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A 182 F 429 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel, Pipe and Forging

Chemical Composition		
Carbon	C %	0.120 max.
Silicon	Si %	0.750 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	14.000 - 16.000
Nickel	Ni %	0.600 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing or Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	415 min.
Yield Strength in Mpa	240 min.
Elongation in %	20 min.
Reduction of Area in %	45 min.
Hardness in HB	190 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S42900	ASTM	USA	Steel, Plate, Sheet and Strip
S42900	UNS	USA	Steel
429	SAE	USA	Steel
STS 429	KS	Korea	Steel, Sheet, Plate and Strip
SUS 429	JIS	Japan	Steel, Sheet, Plate and Strip
A276 429	ASTM	USA	Steel, Bar and Shapes
A959 Type 429	ASTM	USA	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India