

Material: ASTM A 276 S32304

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A 276 S32304 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel, Bar and Shapes

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.500 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	21.500 - 24.500
Nickel	Ni %	3.000 - 5.500
Molybdenum	Mo %	0.050 - 0.600
Nitrogen	N %	0.050 - 0.200
Copper	Cu %	0.050 - 0.600
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
	Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	600 min.
Yield Strength in Mpa	400 min.
Elongation in %	25 min.
Reduction of Area in %	-
Hardness in HB	290 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S32304	ASTM	USA	Steel, Plate, Sheet and Strip
S32304	UNS	USA	Steel
A789 S32304	ASTM	USA	Steel and Tube
A790 S32304	ASTM	USA	Steel and Tube
A928 S32304	ASTM	USA	Steel and Pipe
S32304	AS	Australia	Steel, Sheet, Plate and Strip
SA-276 S32304	ASME	USA	Steel, Bar and Shapes

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India