

Material: ASTM A 276 S44700

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A 276 S44700 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel, Bar and Shapes

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	0.300 max.		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	28.000 - 30.000		
Molybdenum	Mo %	3.500 - 4.200		
Nickel	Ni %	0.150 max.		
Nitrogen	N %	0.020 max.		
Copper	Cu %	0.150 max.		
C + N	C% + N%	0.025 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	480 min.
-	-	-	Yield Strength in Mpa	415 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	217 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S44700	ASTM	USA	Steel, Plate, Sheet and Strip
S44700	UNS	USA	Steel
A176 S44700	ASTM	USA	Steel, Sheet, Plate and Strip
A479 S44700	ASTM	USA	Steel
A493 S44700	ASTM	USA	Steel, Wire, Rod and Forging
A580 S44700	ASTM	USA	Steel and Pipe
SA-276 S44700	ASME	USA	Steel, Bar and Shapes

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com