

# Material: ASTM A 29 1006

## Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets, Tubing

**Group:** Ferrous Mild Steel Alloys

**Sub Group:** ASTM A 29 1006 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Bars, Wire Rods, Plates, Strip, Sheets and Tubing

| Chemical Composition |      |                | Heat Treatment                                                |           |
|----------------------|------|----------------|---------------------------------------------------------------|-----------|
| Carbon               | C %  | 0.080 max.     | As Raw or Annealing or Normalizing or Hardening and Tempering |           |
| Manganese            | Mn % | 0.250 - 0.400  |                                                               |           |
| Phosphorus           | P %  | 0.040 max.     |                                                               |           |
| Sulphur              | S %  | 0.050 max.     |                                                               |           |
| Boron                | B %  | 0.0005 - 0.003 |                                                               |           |
| Copper               | Cu % | 0.200 max.     |                                                               |           |
| Niobium              | Nb % | 0.025 max.     |                                                               |           |
| Vanadium             | V %  | 0.050 max.     |                                                               |           |
| Silicon              | Si % | 0.100 max.     |                                                               |           |
| Aluminium            | Al % | 0.020 max.     |                                                               |           |
| Iron                 | Fe % | Balance        | Mechanical Properties                                         |           |
| -                    | -    | -              | Tensile Strength in Mpa                                       | 300 - 330 |
| -                    | -    | -              | Yield Strength in Mpa                                         | 170 min.  |
| -                    | -    | -              | Elongation in %                                               | 20 min.   |
| -                    | -    | -              | Reduction of Area in %                                        | 45 - 55   |
| -                    | -    | -              | Hardness in HB                                                | 86 - 95   |
| -                    | -    | -              | Impact in Joule                                               | -         |

| Cross Reference Table |          |         |                                                   |
|-----------------------|----------|---------|---------------------------------------------------|
| Material              | Standard | Country | Grade Belong to the Industry                      |
| G10060                | UNS      | USA     | Bars, Wire Rods, Plates, Strip, Sheets and Tubing |
| 10060                 | SAE      | USA     | Bars, Wire Rods, Plates, Strip, Sheets and Tubing |
| 1006                  | AISI     | USA     | Bars, Wire Rods, Plates, Strip, Sheets and Tubing |
| A 1040 1006           | ASTM     | USA     | Bars, Wire Rods, Plates, Strip, Sheets and Tubing |
| A 510 1006            | ASTM     | USA     | Bars, Wire Rods, Plates, Strip, Sheets and Tubing |
| A 830 1006            | ASTM     | USA     | Bars, Wire Rods, Plates, Strip, Sheets and Tubing |
| A 830 G10600          | ASTM     | USA     | Bars, Wire Rods, Plates, Strip, Sheets and Tubing |

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)