

Material: ASTM A 29 1015

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 29 1015 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.130 - 0.180	As Cast or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.300 - 0.600		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Aluminium	Al %	0.020 max.		
Boron	B %	0.0005 - 0.0030		
Copper	Cu %	0.200 max.		
Niobium	Nb %	0.025 max.		
Vanadium	V %	0.050 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 310 - 655 Yield Strength in Mpa 190 min. Elongation in % 5 min. Reduction of Area in % 40 - 50 Hardness in BHN 241 max. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AW1	BS	British	Casting
1015	SAE	USA	Casting
1015	AISI	USA	Casting
A 1040 1015	ASTM	USA	Casting
A 108 Grade 1015	ASTM	USA	Casting
A 510 1015	ASTM	USA	Casting
A 512 Grade 1015	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com