

Material: ASTM A 29 1020

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 29 1020 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Bar

Chemical Composition		
Carbon	C %	0.180 - 0.230
Manganese	Mn %	0.300 - 0.600
Phosphorus	P %	0.040 max.
Sulphur	S %	0.050 max.
Aluminium	Al %	0.020 max.
Boron	B %	0.0005 - 0.003
Copper	Cu %	0.200 max.
Niobium	Nb %	0.025 max.
Silicon	Si %	0.100 max.
Vanadium	V %	0.050 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Raw or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	330 - 690
Yield Strength in Mpa	195 min.
Elongation in %	5 min.
Reduction of Area in %	40 - 50
Hardness in HB	111 - 121
Impact in Joule	47.6 - 69.7 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10200	UNS	USA	Bars, Wire Rods and Tubing
1020	SAE	USA	Sheet, Strip and Plate
1020	AISI	USA	Sheet, Strip and Plate
A 1040 1020	ASTM	USA	Steel
A 108 Grade 1020	ASTM	USA	Steel and Bar
A 29 M1020	ASTM	USA	Steel and Bar
A 510 1020	ASTM	USA	Wire Rod and Round Wire

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India