

# Material: ASTM A 29 1039

## Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

**Group:** Ferrous Mild Steel Alloys

**Sub Group:** ASTM A 29 1039 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Steel and Bar

Chemical Composition		
Carbon	C %	0.370 - 0.440
Manganese	Mn %	0.700 - 1.000
Phosphorus	P %	0.040 max.
Sulphur	S %	0.050 max.
Boron	B %	0.0005 - 0.003
Aluminium	Al %	0.020 max.
Copper	Cu %	0.200 max.
Niobium	Nb %	0.015 max.
Silicon	Si %	0.100 max.
Vanadium	V %	0.020 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As Raw or Annealing or Normalizing or Hardening and Tempering	

Mechanical Properties	
Tensile Strength in Mpa	560 - 610
Yield Strength in Mpa	300 min.
Elongation in %	12 min.
Reduction of Area in %	35 - 40
Hardness in HB	156 - 179
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10390	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1039	SAE	USA	Steel
1039	AISI	USA	Steel and Bar
A 1040 1039	ASTM	USA	Steel
A 510 1039	ASTM	USA	Wire Rod and Round Wire
A 576 10L39	ASTM	USA	Steel and Bar
A 830 1039	ASTM	USA	Plates and Steel

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India