

# Material: ASTM A 29 1043

## Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bar

**Group:** Ferrous Mild Steel Alloys

**Sub Group:** ASTM A 29 1043 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bar

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Bar

Chemical Composition		
Carbon	C %	0.400 - 0.470
Manganese	Mn %	0.700 - 1.000
Phosphorus	P %	0.040 max.
Sulphur	S %	0.050 max.
Boron	B %	0.0005 - 0.003
Copper	Cu %	0.200 max.
Silicon	Si %	0.100 max.
Aluminium	Al %	0.020 max.
Niobium	Nb %	0.015 max.
Vanadium	V %	0.020 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As Raw or Annealing or Normalizing or Hardening and Tempering	

Mechanical Properties	
Tensile Strength in Mpa	570 - 630
Yield Strength in Mpa	310 min.
Elongation in %	12 min.
Reduction of Area in %	35 - 45
Hardness in HB	163 - 179
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10430	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1043	SAE	USA	Steel
1043	AISI	USA	Bar
A 1040 1043	ASTM	USA	Steel
A 510 1043	ASTM	USA	Wire Rod
A 576 10L43	ASTM	USA	Steel and Bar
A 830 1043	ASTM	USA	Plate and Steel

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India