

Material: ASTM A 351 Grade CN7M

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A 351 Grade CN7M Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.070 max.
Silicon	Si %	1.500 max.
Manganese	Mn %	1.500 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.040 max.
Chromium	Cr %	19.000 - 22.000
Molybdenum	Mo %	2.000 - 3.000
Nickel	Ni %	27.500 - 30.500
Copper	Cu %	3.000 - 4.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Cast or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	425 min.
Yield Strength in Mpa	170 min.
Elongation in %	35 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
332C11	BS	British	Casting
Z 2 NCDU 25.20.04 M	AFNOR NF	France	Casting
2074/H9A	AS	Australia	Casting
A 743 Grade CN-7M	ASTM	USA	Casting
A 743 N08007	ASTM	USA	Casting
A 744 Grade CN-7M	ASTM	USA	Casting
SA-351 Grade CN7M	ASME	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India