

# Material: ASTM A 352 Grade LC3

## Standard Specification for Steel Castings for Pressure Purposes

**Group:** Ferrous Mild Steel Alloys

**Sub Group:** ASTM A 352 Grade LC3 Steel Castings for Pressure Purposes

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Casting

Chemical Composition		
Carbon	C %	0.150 max.
Silicon	Si %	0.600 max.
Manganese	Mn %	0.500 - 0.800
Phosphorus	P %	0.040 max.
Sulphur	S %	0.045 max.
Nickel	Ni %	3.000 - 4.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Normalizing or Quenching or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	485 - 655
Yield Strength in Mpa	275 min.
Elongation in %	24 min.
Reduction of Area in %	35 min.
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 G9Ni14	BS	British	Plate, Tubes and Forging
G9Ni14	ISO	International	Casting
1.5638	ISO	International	Casting
A 352 J31550	ASTM	USA	Casting
G 9 Ni 14	CSN	Czech Republic	Casting
G 9 Ni 14	EN	European Union	Casting
G 9 Ni 14	DIN	Germany	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India