

Material: ASTM A 512 Grade 1016

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Tubing

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 512 Grade 1016 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Tubing

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.130 - 0.180	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.045 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 462 - 689 Yield Strength in Mpa 421 min. Elongation in % 13 min. Reduction of Area in % - Hardness in HRC 70 - 100 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10160	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1016	SAE	USA	Bars, Wire Rods and Tubing
1016	AISI	USA	Tubing
A 1040 1016	ASTM	USA	Steel
A 108 Grade 1016	ASTM	USA	Steel and Bar
A 29 1016	ASTM	USA	Steel and Bar
A 510 1016	ASTM	USA	Wire Rods

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com