

Material: ASTM A 513 Grade 1019

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Tubing

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 513 Grade 1019 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Tubing

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 -0.200	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.700 - 1.000		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 410 - 460 Yield Strength in Mpa 220 min. Elongation in % 15 min. Reduction of Area in % 40 - 50 Hardness in HB 116 - 131 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10190	UNS	USA	Bars, Wire Rods and Tubing
1019	SAE	USA	Steel
1019	AISI	USA	Tubing
A 1040 1019	ASTM	USA	Steel
A 29 1019	ASTM	USA	Steel and Bar
A 510 1019	ASTM	USA	Wire Rod and Round Wire
A 512 Grade 1019	ASTM	USA	Tubing

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com