

Material: ASTM A 713 Grade 1075

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 713 Grade 1075 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.700 - 0.800	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.400 - 0.700		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 1025 min. Yield Strength in Mpa 696 min. Elongation in % 17.6 min. Reduction of Area in % 58.2 min. Hardness in BHN - Impact in Joule 21.7 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10750	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1075	SAE	USA	Steel
1075	AISI	USA	Steel and Bar
A 1040 1075	ASTM	USA	Steel
A 29 1075	ASTM	USA	Steel and Bar
A 510 1075	ASTM	USA	Steel
A 713 G10750	ASTM	USA	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com