

Material: ASTM A 988 S32760

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A 988 S32760 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.030 max.
Sulphur	S %	0.010 max.
Chromium	Cr %	24.000 - 26.000
Nickel	Ni %	6.000 - 8.00
Molybdenum	Mo %	3.000 - 4.000
Nitrogen	N %	0.200 - 0.300
Copper	Cu %	0.500 - 1.000
Tungsten	W %	0.500 - 1.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment	
Solution Annealing	
Mechanical Properties	
Tensile Strength in Mpa	750 - 895
Yield Strength in Mpa	550 min.
Elongation in %	25 min.
Reduction of Area in %	45 min.
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S32760	ASTM	USA	Steel, Plate, Sheet and Strip
S32760	UNS	USA	Steel
A276 S32760	ASTM	USA	Steel, Bar and Shapes
A789 S32760	ASTM	USA	Steel and Tube
A790 S32760	ASTM	USA	Steel and Pipe
A815 S32760	ASTM	USA	Steel and Pipe
A959 S32760	ASTM	USA	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India