

Material: ASTM A217 Grade WC11

Standard Specification for Steel Castings, Martensitic Stainless and Alloy, for Pressure-Containing Parts, Suitable for High-Temperature Service

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A217 / A217M Steel Castings, Martensitic Stainless and Alloy, for Pressure-Containing Parts, Suitable for High-Temperature Service

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 - 0.210	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.300 - 0.600		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	1.000 - 1.500		
Nickel	Ni %	0.500 max.		
Molybdenum	Mo %	0.450 - 0.650		
Copper	Cu %	0.350 max.		
Aluminium	Al %	0.010 max.		
Vanadium	V %	0.030 max.	Mechanical Properties	
Other	Ot %	1.000 max.	Tensile Strength in Mpa	550 - 725
Iron	Fe %	Balance	Yield Strength in Mpa	345 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	45 min.
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J11872	UNS	USA	Casting
SA-217 Grade WC11	ASME	USA	Casting
G 17 CrMo 5-5	AFNOR NF	France	Steel
A426 Grade CP11	ASTM	USA	Steel
621	BS	British	Plate
G S 17 CrMo 5-5	DIN	Germany	Casting
G S 17 CrMo 5-5	EN	European Union	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com