

Material: ASTM A240 UNS N08800

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Steel, Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	19.000 - 23.000		
Nickel	Ni %	30.000 - 35.000		
Copper	Cu %	0.750 max.		
Aluminium	Al %	0.150 - 0.600	Mechanical Properties	
Titanium	Ti %	0.150 - 0.600	Tensile Strength in Mpa	520 min.
Iron	Fe %	39.500 min.	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
UNS N08800	UNS	USA	Steel
A358 N08800	ASTM	USA	Steel
A959 Type 800	ASTM	USA	Steel
1.4958	EN	European Union	Flat and Steel
1.4958	DIN	Germany	Flat and Steel
A358 N08810	ASTM	USA	Steel and Pipe
A959 N08811	ASTM	USA	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 **Email:** info@icastllp.com