

Material: ASTM A240 UNS S20153

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Steel, Plate, Sheet and Strip

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	0.750 max.
Manganese	Mn %	6.400 - 7.500
Phosphorus	P %	0.045 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	16.000 - 17.500
Nickel	Ni %	4.000 - 5.000
Nitrogen	N %	0.100 - 0.250
Copper	Cu %	1.000 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
Solution Annealing	
Mechanical Properties	
Tensile Strength in Mpa	655 min.
Yield Strength in Mpa	310 min.
Elongation in %	45 min.
Reduction of Area in %	-
Hardness in HB	241 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4372	DIN	Germany	Steel
SUS 201	JIS	Japan	Steel, Wire and Forging
X12CrMnNiN17-7-5	AFNOR NF	France	Steel
X12CrMnNiN17-7-5	DIN	Germany	Steel
X12CrMnNiN17-7-5	UNI	Italy	Steel, Sheet, Plate and Strip
X12CrMnNiN17 7 5	EN	European Union	Steel
201	SAE	USA	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 **Email:** info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India