

Material: ASTM B 163 N08120

Standard Specification for Seamless Nickel and Nickel Alloy Condenser and Heat-Exchanger Tubes

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 163 N08120 Seamless Nickel and Nickel Alloy Condenser and Heat-Exchanger Tubes

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Tube

Chemical Composition			Chemical Composition		
Carbon	C %	0.020 - 0.100	Nickel	Ni %	35.000 - 39.000
Silicon	Si %	1.000 max.	Iron	Fe %	Balance
Manganese	Mn %	1.500 max.	-	-	-
Molybdenum	Mo %	2.500 max.	-	-	-
Sulphur	S %	0.030 max.	-	-	-
Chromium	Cr %	23.000 - 27.000	Heat Treatment		
Aluminium	Al %	0.400 max.	As-Cast or Annealing or Age Hardning		
Phosphorus	P %	0.040 max.	Mechanical Properties		
Titanium	Ti %	0.200 max.	Tensile Strength in Mpa	620 min.	
Copper	Cu %	0.500 max.	Yield Strength in Mpa	276 min.	
Boron	B %	0.010 max.	Elongation in %	30 min.	
Cobalt	Co %	3.000 max.	Reduction of Area in %	-	
Niobium	Nb %	0.400 - 0.900	Hardness in BHN	-	
Tungsten	W %	2.500 max.	Impact in Joule	-	
Nitrogen	N %	0.130 - 0.300			

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 407 N08120	ASTM	USA	Pipe and Tube
B 408 N08120	ASTM	USA	Rod and Bar
B 409 N08120	ASTM	USA	Plate, Sheet and Strip
B 564 N08120	ASTM	USA	Forging
SB-163 N08120	ASME	USA	Tube
N08120	UNS	USA	Forging
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com