

Material: ASTM B 163 N08801

Standard Specification for Seamless Nickel and Nickel Alloy Condenser and Heat-Exchanger Tube

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 163 N08801 Seamless Nickel and Nickel Alloy Condenser and Heat-Exchanger Tube

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.500 max.		
Copper	Cu %	0.500 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	19.000 - 22.000		
Titanium	Ti %	0.750 - 1.500		
Iron	Fe %	39.500 max.		
Nickel	Ni %	30.000 - 35.000		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	448 min.
-	-	-	Yield Strength in Mpa	172 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 407 N08801	ASTM	USA	Pipe and Tube
SB-163 N08801	ASME	USA	Tube
N08801	UNS	USA	Tube
SB-407 N08801	ASTM	USA	Pipe and Tube
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com