

Material: ASTM B 167 N06617

Standard Specification for Nickel-Chromium-Iron Alloys and Nickel-Chromium-Cobalt-Molybdenum Alloy Seamless Pipe and Tube

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 167 N06617 Nickel-Chromium-Iron Alloys and Nickel-Chromium-Cobalt-Molybdenum Alloy Seamless Pipe and Tube

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Pipe and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.150	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Copper	Cu %	0.500 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	20.000 - 24.000		
Aluminium	Al %	0.800 - 1.500		
Boron	B %	0.006 max.		
Iron	Fe %	3.000 max.		
Molybdenum	Mo %	8.000 - 10.000		
Cobalt	Co %	10.000 - 15.000	Mechanical Properties	
Titanium	Ti %	0.600 max.	Tensile Strength in Mpa	665 - 760
Nickel	Ni %	44.500 min.	Yield Strength in Mpa	240 min.
-	-	-	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 166 N06617	ASTM	USA	Rod, Bar and Wire
B 168 N06617	ASTM	USA	Plate, Sheet and Strip
B 564 N06617	ASTM	USA	Forging
B 626 N06617	ASTM	USA	Tube
B 546 N06617	ASTM	USA	Pipe
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com