

Material: ASTM B 168 N06603

Standard Specification for Nickel-Chromium-Iron Alloys and Nickel-Chromium-Cobalt-Molybdenum Alloy Plate, Sheet and Strip

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 168 N06603 Nickel-Chromium-Iron Alloys and Nickel-Chromium-Cobalt-Molybdenum Alloy Plate, Sheet and Strip

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.400	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.150 max.		
Copper	Cu %	0.500 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	24.000 - 26.000		
Iron	Fe %	8.000 - 11.000		
Phosphorus	P %	0.020 max.		
Aluminium	Al %	2.400 - 3.000		
Titanium	Ti %	0.100 - 0.250		
Zirconium	Zr %	0.010 - 0.100	Mechanical Properties Tensile Strength in Mpa 650 min. Yield Strength in Mpa 300 min. Elongation in % 25 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Yttrium	Y %	0.010 - 0.150		
Nickel	Ni %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 163 N06603	ASTM	USA	Tube
N06603	UNS	USA	Tube
B 166 N06603	ASTM	USA	Rod, Bar and Wire
B 167 N06603	ASTM	USA	Pipe and Tube
B 516 N06603	ASTM	USA	Tube
B 517 N06603	ASTM	USA	Pipe
B 564 N06603	ASTM	USA	Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com