

Material: ASTM B 407 N08811

Standard Specification for Nickel-Iron-Chromium Alloy Seamless Pipe and Tube

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 407 N08811 Nickel-Iron-Chromium Alloy Seamless Pipe and Tube

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Pipe and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 - 0.100	As-Cast or Annealing or Age Hardning	
Chromium	Cr %	19.000 - 23.000		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.500 max.		
Aluminium	Al %	0.150 - 0.600		
Sulphur	S %	0.015 max.		
Copper	Cu %	0.750 max.		
Titanium	Ti %	0.150 - 0.600		
Iron	Fe %	39.500 max.		
			Mechanical Properties	
Al + Ti	Al % + Ti %	0.850 - 1.200	Tensile Strength in Mpa	450 min.
Nickel	Ni %	30.000 - 35.000	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 163 N08811	ASTM	USA	Tube
B 408 N08811	ASTM	USA	Rod and Bar
B 409 N08811	ASTM	USA	Plate, Sheet and Strip
B 564 N08811	ASTM	USA	Forging
SB-163 N08811	ASME	USA	Tube
N08811	UNS	USA	Tube
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India