

Material: ASTM B 564 N08120

Standard Specification for Nickel Alloy Forgings

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 564 N08120 Nickel Alloy Forgings

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Forging

Chemical Composition		
Carbon	C %	0.020 - 0.100
Silicon	Si %	1.000 max.
Manganese	Mn %	1.500 max.
Chromium	Cr %	23.000 - 27.000
Sulphur	S %	0.030 max.
Copper	Cu %	0.500 max.
Phosphorus	P %	0.040 max.
Aluminium	Al %	0.400 max.
Titanium	Ti %	0.200 max.
Nb + Ta	Nb% + Ta%	0.400 - 0.900
Molybdenum	Mo %	2.500 max.
Tungsten	W %	2.500 max.
Cobalt	Co %	3.000 max.
Nitrogen	N %	0.150 - 0.300
Boron	B %	0.010 max.

Chemical Composition		
Nickel	Ni %	35.000 -
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
Heat Treatment		
As-Cast or Annealing or Age Hardning		
Mechanical Properties		
Tensile Strength in Mpa	621 min.	
Yield Strength in Mpa	276 min.	
Elongation in %	30 min.	
Reduction of Area in %	-	
Hardness in BHN	-	
Impact in Joule	-	

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 163 N08120	ASTM	USA	Tube
B 407 N08120	ASTM	USA	Pipe and Tube
B 408 N08120	ASTM	USA	Rod and Bar
B 409 N08120	ASTM	USA	Plate, Sheet and Strip
SB-163 N08120	ASME	USA	Tube
N08120	UNS	USA	Forging
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com