

Material: ASTM B 564 N08367

Standard Specification for Nickel Alloy Forgings

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 564 N08367 Nickel Alloy Forgings

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Chromium	Cr %	20.000 - 22.000		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	6.000 - 7.000		
Phosphorus	P %	0.040 max.		
Nitrogen	N %	0.180 - 0.250		
Copper	Cu %	0.750 max.		
Nickel	Ni %	23.500 - 25.500		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	655 min.
-	-	-	Yield Strength in Mpa	310 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 688 N08367	ASTM	USA	Plate, Sheet and Strip
B 691 N08367	ASTM	USA	Rod, Bar and Wire
B 462 N08367	ASTM	USA	Pipe Flanges, Forged Fittings, and Valve
A 314 N08367	ASTM	USA	Bar and Forging
B 472 N08367	ASTM	USA	Billet and Bar
B 690 N08367	ASTM	USA	Pipe and Tube
B 834 N08367	ASTM	USA	Pipe Flanges, Forged Fittings, and Valve

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com