Material: ASTM B 564 N10665

Standard Specification for Nickel Alloy Forgings

Group: *Non-Ferrous Nickel Alloys*
Sub Group: *ASTM B 564 N10665 Nickel Alloy Forgings*
Application: *Intended for Valve, Pump, General Engineering, Automotive and other Industries*
Grade Belongs to the Industry: *Forging*

Chemical Composition		
Carbon	C %	0.020 max.
Silicon	Si %	0.100 max.
Manganese	Mn %	1.000 max.
Chromium	Cr %	1.000 max.
Sulphur	S %	0.030 max.
Molybdenum	Mo %	26.000 - 30.000
Phosphorus	P %	0.040 max.
Cobalt	Co %	1.000 max.
Iron	Fe %	1.000 - 6.000
Nickel	Ni %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	760 min.
Yield Strength in Mpa	350 min.
Elongation in %	40 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
B 333 N10665	ASTM	USA	Plate, Sheet and Strip
B 335 N10665	ASTM	USA	Rod
B 462 N10665	ASTM	USA	Pipe and Valve
B 619 N10665	ASTM	USA	Pipe
B 622 N10665	ASTM	USA	Pipe and Tube
B 626 N10665	ASTM	USA	Tube
-	-	-	-

Disclaimer: *All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.*
Customer Care: +91-99090 45075 Email: info@icastllp.com