

Material: ASTM B 572 N06002

Standard Specification for Nickel-Iron-Chromium-Molybdenum Alloy Rod

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 572 N06002 Nickel-Iron-Chromium-Molybdenum Alloy Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.150	As-Cast or Annealing or Age Hardening	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	20.500 - 23.000		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	8.000 - 10.000		
Phosphorus	P %	0.040 max.		
Cobalt	Co %	0.500 - 2.500		
Iron	Fe %	17.000 - 20.000		
Tungsten	W %	0.200 - 1.000		
Nickel	Ni %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	660 min.
-	-	-	Yield Strength in Mpa	240 min.
-	-	-	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 619 N06002	ASTM	USA	Pipe
B 622 N06002	ASTM	USA	Pipe and Tube
B 626 N06002	ASTM	USA	Tube
B 435 N06002	ASTM	USA	Plate, Sheet and Strip
B 472 N06002	ASTM	USA	Billets and Bars
SB-619 N06002	ASME	USA	Pipe
SB-622 N06002	ASME	USA	Pipe and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com