

Material: ASTM B 574 N06035

Standard Specification for Low-Carbon Nickel-Chromium-Molybdenum, Alloy Rod

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 574 N06035 Low-Carbon Nickel-Chromium-Molybdenum, Alloy Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	32.250 - 34.250		
Sulphur	S %	0.015 max.		
Molybdenum	Mo %	7.600 - 9.000		
Phosphorus	P %	0.030 max.		
Cobalt	Co %	1.000 max.		
Copper	Cu %	0.300 max.		
Aluminium	Al %	0.400 max.		
Iron	Fe %	2.000 max.	Mechanical Properties	
Tungsten	W %	0.600 max.	Tensile Strength in Mpa	586 min.
Vanadium	V %	0.200 max.	Yield Strength in Mpa	241 min.
Nickel	Ni %	Balance	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N06035	ASTM	USA	Forging
B 575 N06035	ASTM	USA	Plate, Sheet and Strip
B 462 N06035	ASTM	USA	Pipe Flanges, Forged Fittings and Valve
B 619 N06035	ASTM	USA	Pipe
B 622 N06035	ASTM	USA	Pipe and Tube
B 626 N06035	ASTM	USA	Tube
B 472 N06035	ASTM	USA	Billets and Bars

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India